



# White Polyimide Coverlay Film

**White Polyimide Coverlay** is made of WHITE polyimide film coated by modified stage-B acrylic adhesive on one side with protection release film or paper, widely used in protection of FCPB.

## Characters:

- \* Excellent dielectric performance, high bondability and good dimension stability
- \* Low fluidity and good processability.
- \* In WHITE colour
- \* Supplied with different sizes

## Spec.:

Models AD/PI/AD (AD=adhesive;PI=polyimide film)	Unit	25/40/0
Typical Thickness	mm±10%	0.065
Film Thickness	mm	0.040
Adhesive thickness	mm	0.025
Supply Size and Packing	Standard roll: 50m <sup>2</sup> per roll,width:500mm Carton after winded up into log roll and sealed by plastic film bag, Core ID:3"	

∩ customization can also be available.

## Typical Properties( The follows are just examples not read as guaranteed values)

Items	Unit	Test Method	Typical datas
1. Peel Strength -As normal conditions -After soldering	N/mm--width	IPC-TM-650-2.4.9	1.0 1.0
2. Dimensional Stability	%	IPC-TM-650-2.2.4A	0.10
3. Adhesive Flow max.(overflow)	um	IPC-TM-650-2.3.17.1	<127
4. Volatile Content	%	IPC-TM-650-2.3.37	≤3.0
5. Soldering resistance	288℃/10sec.	IPC-TM-650-2.4.13	Pass
6. Moisture Absorption	%	IPC-TM-650-2.6.2	≤4.0
7. Dielectric strength	KV/mm	ASTM-D-149	≥70
8. Chemical resistance	%	IPC-TM-650-2.3.2	≥80
9. Dielectric constant	MHZ	IPC-TM-650-2.5.5.3	≤4.0
10.Dissipation factor	-----	IPC-TM-650-2.5.5.3	≤0.04
11. Volume resistivity	MΩ-cm	IPC-TM-650-2.5.17	10 <sup>8</sup>
12. Surface resistivity	MΩ	IPC-TM-650-2.5.17	10 <sup>6</sup>

## Storage:

The product is packed in reinforced carton and sealed in plastic film bag. Please keep dry and in room temperature. Shelf life is 12 months.

*Note: 1.All of above information is based on our best knowledge, not read as guarantees. Right reserved for corrections.  
2.Please contact us if customization requirements.*

**Contact information:** Company: WJF Chemicals Co. Ltd. QuZhou (website: <http://www.wjfchemicals.com>)

Address: 601 ZhongXing Plaza No. 123 HeHua ZhongLu QuZhou ZheJiang Province China  
Email: [info@wjfchemicals.com](mailto:info@wjfchemicals.com) Tel./Fax: +865703865831 Mob.:+8613059765326

